

PMMA XT Extruded acrylic sheets

DESCRIPTION

PMMA EXTRUDED SHEETS are produced according to the ISO 7823-2:2003 standard and can be used both indoor and outdoor for a wide variety of domestic and industrial applications.

PMMA XT is available in wide range of thicknesses, translucent and opaque colors, textures, special effects and high impact grades (OPTIX XT Super).

The complete range offers high transparency, inherent UV resistance, weathering and ageing resistance and can be easily machined or thermoformed by standard techniques.

TYPICAL PROPERTY VALUES

Properties	Method	Units	OPTIX XT (R7000)
General			
Density	ISO 1183	g/cm ³	1.19
Water Absorption	ISO 62 (1)	%	0.3
Mechanical			
Tensile Strength	ISO 527-2	MPa	72
Elongation at break	ISO 527-2	%	4
Tensile Modulus	ISO 527-2	MPa	3300
Flexural Strength	ISO 178	MPa	106
Flexural Modulus	ISO 178	MPa	3350
Compressive Strength	ISO 604	MPa	117
Rockwell Hardness	M scale		95
Impact Resistance (Charpy unnotched)	ISO 179/1fu	kJ/m ²	15
Impact Resistance (Charpy notched)	ISO 179/1eA	kJ/m ²	2
Impact Resistance (Izod notched)	ISO 180/1A	kJ/m ²	1.5
Optical			
Refractive Index	ISO 489		1.49
Light Transmission (3mm transparent sheet)	ASTM D1003	%	92
Haze (3mm transparent sheet)	ASTM D1003	%	< 1
Thermal			
Vicat Softening Temp.(50N)	ISO 306	°C	105
Heat Deflection Temp. (1.82 MPa)	ISO 75-1	°C	95
Coeff. of Linear Thermal Expansion	DIN 53483		0.04
Thermal Conductivity	ASTM C177	W/mK	0.19
Maximum Continuous Service Temp.		°C	70
Maximum Short Time Service Temp.		°C	90
Minimum Temp.		°C	-40
Electrical			
Dielectric Strength	DIN 53481	kV/mm	20-25
Dielectric Constant (50Hz)	DIN 53483		3.7
Dissipation Factor tanδ (1 MHz)	DIN 53483		0.04
Surface Resistivity	IEC 60093	Ohm	>10 ¹⁴
Volume Resistivity	IEC 60093	Ohm.cm	>10 ¹⁵



VINK Plastics Spain S.L.U.

C/. Bosquerons 3, Nave 1. 08170 Montornès del Vallès. Barcelona - Spain
T. +34 935 683 961 | info@vink.es
www.vink.es



PMMA XT Extruded acrylic sheets

PMMA XT Super - Extruded High Impact Acrylic Sheets

Properties	Method	Units	S25 (R7700)	S30 (R7400)	S50 (R7500)	S75 (R7800)	S100 (R7600)
General							
Density	ISO 1183	g/cm ³	1.19	1.19	1.18	1.17	1.16
Water Absorption	ISO 62 (1)	%	0.3	0.3	0.3	0.3	0.3
Mechanical							
Tensile Strength	ISO 527-2	MPa	57	54	50	45	40
Elongation at break	ISO 527-2	%	22	26	30	35	40
Tensile Modulus	ISO 527-2	MPa	2450	2275	2100	1900	1700
Flexural Strength	ISO 178	MPa	88	84	79	71	62
Flexural Modulus	ISO 178	MPa	2470	2285	2100	1950	1800
Rockwell Hardens	M scale		77	73	68	56	44
Impact Resistance (Charpy unnotched)	ISO 179/1fu	kJ/m ²	51	59	67	71.5	76
Impact Resistance (Charpy notched)	ISO 179/1eA	kJ/m ²	4.3	5.3	6.2	6.9	7.6
Impact Resistance (Izod notched)	ISO 180/1A	kJ/m ²	4	4.5	5	5.6	6.3
Optical							
Refractive Index	ISO 489		1.49	1.49	1.49	1.49	1.49
Light Transmission (3mm transparent sheet)	ASTM D1003	%	92	92	92	92	92
Haze (3mm transparent sheet)	ASTM D1003	%	< 2.7	< 2.7	< 2.7	< 2.7	< 2.7
Thermal							
Vicat Softening Temp.(50N)	ISO 306	°C	99	98	97	94	90
Heat Deflection Temp. (1.82 MPa)	ISO 75-1	°C	92	91	90	85	83
Coeff. of Linear Thermal Expansion	ISO 11359-2	µm/m°C	70	80	100	105	110
Maximum Continuous Service Temp.		°C	65	63	63	62	62
Maximum Short Time Service Temp.		°C	86	83	81	76	74
Minimum Temp.		°C	-20	-20	-20	-20	-20

DIMENSIONS

Thickness, mm	Width, mm	Length, mm
0.70 - 30.0	1000, 1220 and 2050	600 - 6000

Sheets are also available cut to size, according to customer requirements.



VINK Plastics Spain S.L.U.

C/. Bosquerons 3, Nave 1. 08170 Montornès del Vallès. Barcelona - Spain
 T. +34 935 683 961 | info@vink.es
 www.vink.es



PMMA XT Extruded acrylic sheets

TOLERANCES FOR DIMENSIONS

Sheet Thickness, mm	Thickness, %	Width Tolerances, mm	Length Tolerances, mm	Diagonals Tolerances, mm	Flatness Tolerances
<1.5	± 8	Sheets cut in production: -0.0 /+3.0	Sheets cut in production: -0.0 /+3.0	Sheets cut in production: Length ≥ 4000 mm - ≤ 2 Length ≥ 4000 mm - ≤ 4	Max. allowed bowing - 0.5% from linear dimensions. Max. allowed bowing across the width of the sheet - ≤ 5 mm per meter of width. Max. allowed bowing along the length of the sheet - ≤ 5 mm per meter of length.
≥ 1.5, < 2.0	± 4				
≥ 2.0, < 15.0	± 3				
≥ 15.0, < 20.0	± 5	Sheets cut to size: ± 0.50	Sheets cut to size: ± 0.50	Sheets cut to size: ≤ 0.5	
≥ 20.0	± 10				

COLORS

PMMA XT sheets are naturally colorless and exceptionally clear, however pigments can be added to obtain a wide range of tints and colors. PMMA XT colored sheets maintain the same light transmission percentages regardless of thickness (except for opals and diffusers).

DEFINITIONS

SHRINKAGE

After heating acrylic extruded sheets will shrink during the cooling process, the shrinkage is higher in the extrusion direction.

This characteristic of PMMA XT should be taken into account when planning the final sheet's dimensions.

Sheet Thickness, mm	Standard Grade		Special Grades *	
	Shrinkage M.D**, %	Shrinkage T.D**, %	Shrinkage M.D**, %	Shrinkage T.D**, %
≥ 1.80, < 2.30	6 - 7	0.5	3 - 4	0.5
≥ 2.30, < 3.50	5 - 6	0.5	2 - 3	0.5
≥ 3.50, < 4.00	3 - 4	0.5	1 - 2	0.5
≥ 4.00, < 6.00	2 - 3	0.5	0 - 1	0.5
≥ 6.00	2	0.5	0 - 1	0.5

* for example Sky Domes grades for use in thermoforming, which are produced upon special request for shrinkage conditions.

** M.D. – Machine (extrusion) direction

T.D. – Transverse (perpendicular to extrusion) direction

FIRE TEST PERFORMANCE

PMMA is a combustible material and will burn if ignited, however, unlike other polymers, does not produce toxic or corrosive gases and produces very little smoke which is an important safety benefit.

OPTIX XT extruded acrylic sheets are classified:

- HB according to UL94.
- E according to UNE-EN ISO 13501.



VINK Plastics Spain S.L.U.

C/. Bosquerons 3, Nave 1. 08170 Montornès del Vallès. Barcelona - Spain

T. +34 935 683 961 | info@vink.es

www.vink.es



PMMA XT Extruded acrylic sheets

NOISE REDUCTION

PMMA XT sheets are used widely as noise-reduction barriers along roads and highways. For more information, see OPTIX XT Acoustic Walls Guidebook.

CHEMICAL RESISTANCE

PMMA XT sheets have good resistance to water, alkalis, aqueous inorganic salt solutions and most common dilute acids. Some substances do not have any effect on OPTIX XT however some can cause staining, swelling, crazing, weakening or even complete dissolving of the material.

Note: Any substance that comes with contact with PMMA should be checked for compatibility.

ENVIRONMENTAL STRESS CRACKING

Environmental Stress Cracking (ESC) is a result of the combination of stress and chemical exposure. The level of stress needed for ESC is lower than the normal failure mechanical stress of PMMA in a chemical-free environment. Stresses can be created during fabrication and forming and can be controlled by an annealing process. Stresses can also be created by improper installation. Cold bended sheets under permanent induced stress or sheets under periodic stress (fatigue) are also susceptible to ESC.

GENERAL GUIDELINES

STORAGE

PMMA XT is a rigid sheet, incorrect handling can cause breakage, leaving sharp edges.

PMMA XT sheets must be stored with their original protective masking in a cool, dry and well-ventilated room, away from direct sunlight, excessive humidity, rain or solvent vapors.

PMMA XT sheets are best stored horizontally on their delivery pallets. Pay attention to avoiding pressure on the unsupported areas. Never leave sheets or pallets uncovered.

PROTECTIVE FILM

Both surfaces of PMMA XT sheet are protected by a fully recyclable polyethylene (PE) film. Keep this film in position as long as possible and remove only and immediately after installation.

There are two kinds of protective film for the sheets:

- Universal film that is suitable for machining
- Easy-removal film that is suitable for sheets where the film will be removed before processing. This type of film is not suitable if machining of the sheet is required to be done with the protective film on the sheet.

Both of the above types of film are suitable for thermoforming and laser cutting.

Printed film must be removed before thermoforming in order to avoid transfer of the printing ink to the sheet's surface.

CLEANING & MAINTENANCE

PMMA XT sheets are produced in clean-room environment and do not need to be cleaned before use. However, cleaning may be needed after fabrication, before sensitive processes such as vacuum metallization or printing or for maintenance during use.

If PMMA XT sheets need to be cleaned, wash the sheet surface with clean fresh water with a mild soap. In order to verify that the soap you are using is compatible with PMMA test a hidden area before cleaning. Use a clean soft cloth or sponge and rinse well. Do not scrub or use brushes. Dry with a soft cloth. The use of window cleaning fluids or solvents such as alcohols, turpentine, acetone, etc., can cause damage to the sheet.



VINK Plastics Spain S.L.U.

C/. Bosquerons 3, Nave 1. 08170 Montornès del Vallès. Barcelona - Spain

T. +34 935 683 961 | info@vink.es

www.vink.es

PMMA XT Extruded acrylic sheets

ENVIRONMENTAL ADVANTAGES

PMMA XT sheets are environmental friendly. LCA (Life Cycle Assessment) and Eco profiles of PMMA sheet production show a low impact on the environment.

The outstanding chemical stability and long-time resistance to aging and weathering of PMMA XT sheets often ensures a long service time. The sheets and their polyethylene protective layers are fully recyclable. They do not contain any toxic materials, halogens or heavy metals, which may cause environmental damage or health risks. PMMA XT sheets do not contain Bisphenol-A. Ozone Depleting Substances

(ODP) are not used in the manufacture of PMMA XT sheets and they do not release pollutant substances into the environment during manufacture. They do not produce toxic or corrosive gases when burning, fires can be extinguished with water.

PMMA XT scrap is not classified as hazardous waste small amounts can be disposed as household refuse. Large quantities should be disposed by recycling.

RE-WORKING

- Handling:

Machining, Assembling, Forming, Glazing and Signage Installation recommendations can be found in the PMMA XT Guidebook.

- Cold bending:

Unlike thermoforming, cold-bended PMMA XT will not keep its form unless installed into a frame. The sheet must be with perfect edges to avoid breakage during bending. The radius of the bend should not be below the minimum value in order to avoid high permanent stress, which can eventually cause small cracks or even break the sheet.

Minimum recommended bend radius is 300 times the thickness of the sheet.



VINK Plastics Spain S.L.U.

C/. Bosquerons 3, Nave 1. 08170 Montornès del Vallès. Barcelona - Spain

T. +34 935 683 961 | info@vink.es

www.vink.es